

Application No. 10/748,649  
Amendment dated October 10, 2007  
Reply to Office Action of August 16, 2007

RECEIVED  
CENTRAL FAX CENTER

OCT 10 2007

**Listing of Claims:**

1. (Previously Presented) A product comprising:
  - a single ply web comprising cellulosic fibers having a first and a second opposing sides;
  - a plurality of extruded filaments of a chemical additive extruded onto the first and/or second opposing side of the web;
  - the single ply web wound into a roll;
  - the roll having a roll bulk about 10 cc/g or greater; and
  - the first and/or second opposing side with the chemical additive filaments having a Fuzz-On-Edge about 1.8 mm/mm or greater.
2. (Withdrawn/Previously Presented) A product comprising:
  - an uncreped throughdried single ply tissue web comprising cellulosic fibers having a first and a second opposing sides;
  - a plurality of extruded filaments of a chemical additive extruded onto the first and/or second opposing side of the web;
  - the tissue web wound into a roll;
  - the roll having a roll bulk about 10 cc/g or greater; and
  - the first and/or second opposing side with the chemical additive filaments having a Fuzz-On-Edge about 2.0 mm/mm or greater.
3. (Original) The product of claim 1 or 2 wherein the roll bulk is about 11 cc/g or greater.
4. (Original) The product of claim 1 or 2 wherein the roll bulk is between about 10 cc/g to about 16 cc/g.

Application No. 10/748,649  
Amendment dated October 10, 2007  
Reply to Office Action of August 16, 2007

5. (Original) The product of claim 1 or 2 wherein the roll bulk is between about 11 cc/g to about 16 cc/g.
6. (Original) The product of claim 1 or 2 wherein the Fuzz-On Edge is about 2.4 mm/mm or greater.
7. (Original) The product of claim 1 or 2 wherein the Fuzz-On Edge is about 2.8 mm/mm or greater.
8. (Original) The product of claim 1 or 2 wherein the Fuzz-On Edge is between about 2.0 mm/mm to about 3.0 mm/mm.
9. (Original) The product of claim 1 or 2 wherein the web comprises a bath tissue web.
10. (Previously Presented) The product of claim 1 or 2 wherein the extruded filaments of the chemical additive are extruded onto both the first and the second opposing sides.
11. (Original) The product of claim 5 wherein the Fuzz-On Edge is between about 2.0 mm/mm to about 3.0 mm/mm.
12. (Original) The product of claim 5 wherein the Fuzz-On Edge is between about 2.2 mm/mm to about 2.9 mm/mm.
13. (Original) The product of claim 1 or 2 wherein the chemical additive comprises polysiloxane.
14. (Original) The product of claim 1 or 2 wherein the Kershaw firmness is between about 12 mm to about 0 mm.
15. (Original) The product of claim 1 or 2 wherein the CD Kawabata Bending Stiffness is about 0.06 or less.
16. (Original) The product of claim 11 wherein the CD Kawabata Bending Stiffness is about 0.04 or less.

Application No. 10/748,649  
Amendment dated October 10, 2007  
Reply to Office Action of August 16, 2007

17. (Previously Presented) The product of claim 1, 2, 5, 10, 11, 13, 14, 15, or 16 wherein the first or second opposing side with the applied chemical contains a plurality of fuzzy fibers generated by a shear calendering device.
18. - 21. (Canceled)
22. (Previously Presented) The product of claim 1 or 2 wherein the chemical additive has a viscosity of between about 1,500 cps to about 10,000 cps.
23. (Previously Presented) The product of claim 1 or 2 wherein the extruded filaments form a network.
24. (Previously Presented) The product of claim 1 or 2 wherein the chemical additive has a viscosity of between about 1,000 cps to about 50,000 cps.
25. (Previously Presented) The product of claim 1 or 2 wherein the extruded filaments of the chemical additive are extruded onto only one opposing side of the web.
26. (Previously Presented) The product of claim 1 or 2 wherein extruded filaments are continuous.
27. (Previously Presented) The product of claim 1 or 2 wherein the extruded filaments are discontinuous.
28. (Previously Presented) The product of claim 1 or 2 wherein the extruded filaments are melt blown.